

More than 32 years of experience
C5 manufactured for an heavy production and significant height above ground

Main advantages

- ◆ Profiling without any angle in order not to damage during mechanical contacts
- ◆ Very high mechanical strength
- ◆ Cross section 68 x 55 – 2.67'' x 2.16'' with drilling in the center of the post to allow a perfect alignment
- ◆ Lateral drilling to position the tension roller
- ◆ Cor-ten aspect adapted to wine tourism regions
- ◆ Sides section 68 mm (2.67'') to optimize the stability of the trellising



Galvanization

C5	Strip Galva Z 275 gr/m2 18-25µ per side En 10 142 Steel DX51-S250 GD			Cor-ten B type Steel S300JOWP			Hot dip galvanization En 1461 60-80µ per side Steel S235 JR En 10 025/En 10 147		
C5 Tecnotestata per bundles 100 pces / Coil 213	Thickness 1.50 0.059"	Thickness 1.80 0.0709"	Thickness 2.00 0.078"	Thickness 1.60 0.063"	Thickness 1.80 0.0709"	Thickness 2.00 0.078"	Thickness 1.65 0.064"	Thickness 1.95 0.076"	Thickness 2.15 0.084"
Weighting per mtr	-	3,01	3,34	-	3,01	3,34	-	3,31	3,68



Installation advice

- ◆ Cap and mini piston on request
- ◆ Plant the post during the wet season
- ◆ Drive 25-30 % of the post length into the ground
- ◆ Deep rip soils during site preparation
- ◆ Drill a pilot hole in difficult ground



Recommendations

- ◆ Row from 100 to 150 mtr 1.8 or 1.95 mm
- ◆ Row more 150 mtr 2.0 or 2.15 mm

Consortium France

Jean-Luc Duboeuf
4381 Route Du Tremblay
F-73 290 La Motte Servolex
Tel : +33 615 93 14 99
jl.duboeuf@consortium73.fr

Consortium S.p.A

Viale Dell'Industria, 26
I - 37038 Soave Verona Italia
Tel : +39 045 610 28 88
info@consortiumspa.net